

Flint Clay/Kaolin

Grade/Particle size (mm)	Analysis item					
	Al ₂ O ₃ (%)	Fe ₂ O ₃ (%)	CaO (%)	H ₂ O (%)	B.D. (g/cm ³)	PH
Calcined kaolin 5-3-1-0, 200F	≥ 45	≤ 1.3	≤ 0.5	≤ 0.3		≤ 10
Calcined kaolin 0-50	≥ 45	≤ 1.6	≤ 0.5	≤ 0.3		≤ 10
Flint clay 0-50	≥ 45	≤ 1.5		≤ 0.5	≥ 2.45	

* These figures are typical specifications. Please inquire for more information.